

# PRINTEX® kappa 220 PWD

## Product Information

0591

### Physico-Chemical Properties

Parameter	Method	Unit	Typical Values
OAN Oil Absorption Number	following ASTM D 2414	ml /100 g	128
BET	following ASTM D 6556	m <sup>2</sup> /g	175
pH	following ASTM D 1512		4
Ash Content	following ASTM D 1506	%	0.02

### 1. General Description

- Gas Black
- Medium Color Gas Type (MCG)

### 2. Chemical Description

Industrially produced Specialty Carbon Black

### 3. Application

Batteries

### 4. Impurity Level

Parameter	Unit	Value
Iron	ppm	<10
As, Cd, Co, Cr, Cu, Mn, Mo, Ni, V, W, Zn	ppm	Sum <20

Those values are typical impurity levels that can be expected. They are not part of any specific tion.

### 5. Forms of Supply

Powder, available in 10 kg paper bags

### 6. Storage Conditions

The high surface area of Specialty Carbon Blacks bears the inherent risk of adsorption of vapors and/or gases, which in turn impacts the product's application relevant properties. It is therefore recommended to always store Specialty Carbon Blacks out of reach of potential contaminants and sources of contamination. Storage temperatures should not exceed 50 °C.

Carbon Black should be stored under cool and dry conditions. Please refer to our Product Safety Data Sheet. Densification or adsorption processes etc. may adversely affect the product's application relevant properties. This also applies to storage in silos or other closed containers.

### 7. Technical Literature

Technical literature on the use of Specialty Carbon Blacks can be ordered at the below mentioned address.



#### The Americas

Orion Engineered Carbons LLC  
1700 City Plaza Drive, Suite 300  
Spring, TX 77389  
USA  
Phone +1 832 445 3300

AMERICAS@orioncarbons.com

#### Europe/ Middle East/ Africa

Orion Engineered Carbons GmbH  
Hahnstraße 49  
60528 Frankfurt am Main  
Germany  
Phone +49 69 36 50 54 100

EMEA@orioncarbons.com

#### Asia Pacific

Orion Engineered Carbons Trading (Shanghai) Co., Ltd.  
BM Intercontinental Business Centre, Room 3701-3702  
100 Yutong Road  
200070 Shanghai, China  
Phone +86 21 6107 0966

APAC@orioncarbons.com

#### Global Corporate Headquarters

Orion Engineered Carbons S.A., 6 Route de Trèves, L-2633 Senningerberg, Luxembourg, Phone +352 27 04 80 60

[www.orioncarbons.com](http://www.orioncarbons.com)

All information and statements contained herein are believed to be accurate, however Orion Engineered Carbons GmbH (as well as all other Orion Engineered Carbons group companies including Orion Engineered Carbons SA), its agents and/or affiliates give no warranty with respect thereto, including but not limited to any results to be obtained or the non-infringement of any proprietary right. Use or application of such information or statements or the material or systems described herein is at user's sole discretion and risk, and consequently user acknowledges that Orion Engineered Carbons GmbH (as well as all other Orion Engineered Carbons group companies including Orion Engineered Carbons SA), its agents and/or affiliates shall bear no responsibility or liability for same. Nothing herein shall be construed as a license of or recommendation for use, especially with concern to the potential infringement of any proprietary right. All sales are subject to the respective Standard Terms & Conditions of Sale issued by Orion Engineered Carbons GmbH or - as the case may be - another Orion Engineered Carbons group company, including but not limited to the Limited Warranty clauses contained therein.

© 2018 Orion Engineered Carbons GmbH

OE-PI 0591-08/2018